

TECHNICAL SPECIFICATION SHEET

MEDITERRANEAN 300



	Casablanca	Monaco	Palermo
Nominal Size	300x300mm		
Number of tiles per covered square metre	11		
Surface Finish	Particle Impregnated Glaze		
Manufacturing Standard	ISO 13006: 1998 - Group AIIa - Part 1		
Deviation in Length and Width (ISO 10545-2)	± 1.25% (Maximum)		
Deviation in Thickness (ISO 10545-2)	± 10% (Maximum)		
Straightness of Sides (ISO 10545-2)	± 0.5% (Maximum)		
Rectangularity (ISO 10545-2)	± 1.0% (Maximum)		
Surface Flatness - Curvature (ISO 10545-2)	± 0.5% (Maximum)		
- Warpage (ISO 10545-2)	± 0.8% (Maximum)		
Surface Quality (ISO 10545-1)	Minimum 95% Conform		
Resistance to Thermal Shock (ISO 10545-9)	Resistant		
Crazing Resistance (Glazed Tiles Only) ISO 10545-11	Resistant		
Chemical Resistance (ISO 10545-13)	Resistant		
Frost Resistance (ISO 10545-12)	Resistant		
Determination of Moisture Expansion (ISO 10545-10)	≤ 0.06%		
Water Absorption (ISO 10545-3)	3% < E ≤ 6%		
Modulus of Rupture (ISO 10545-4)	20 MPa (Minimum Average)		
Breaking Strength (ISO 10545-4)	0.95 kN (Minimum Average)		
Scratch Hardness - MOH's (BS6431 Part 13)	5 (Minimum)		

SAMPLE RANGE RESULTS

Test / Method	Monaco	Casablanca	Palermo
Water Absorption (ISO 10545-3)	4.5%	4.5%	4.5%
Modulus of Rupture (ISO 10545-4)	22.37	22.25	21.9
Breaking Strength (ISO 10545-4)	1.9kN	1.9kN	1.9kN
Scratch Hardness – MOH's (BS6431 Part 13)	8	8	8
Resistance to Surface Abrasion (ISO 10545-7)	4	4	4
Resistance to Deep Abrasion (ISO 10545-6)	N/A	N/A	N/A
Slip Resistance Classifications (AS/NZS 4586:1999)	<i>Mean Range Result</i>		
◆ Appendix A: WET Pendulum (Four S)	Class X		35-44
◆ Appendix B: DRY (FFT) - Tortus	Class F		≥ 0.4
◆ Appendix C: WET/BAREFOOT Ramp	n/a		n/a
◆ Appendix D: OIL-WET Ramp	Class R 10		≥10 <19

SAMPLING: Sampling and the basis for acceptance complied with the requirements of ISO 10545-1.

COMPLIANCE: When tested according to the relevant method indicated in parenthesis, the above results all conform to the requirements of the Manufacturing Standard.

REMARKS ON SLIP RESISTANCE CLASSIFICATIONS (AS/NZS4586:1999): Tiles tested to AS/NZS 4586:1999 'Slip resistance classification of new pedestrian surface materials'. The slip resistance of a surface may change with use either becoming more slippery because of natural polishing, or less due to abrasion and roughening of the surface. The presence of dirt or contaminants may make surfaces more slippery, as can poor maintenance practices.

CLASSIFICATIONS: In order to interpret the classifications, please refer to Standards Australia Handbook 197 'An introductory guide to the slip resistance of pedestrian surface materials' which recommends minimum classifications for a wide variety of locations. It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where propriety surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.

REMARKS ON THE MOISTURE EXPANSION OF CERAMIC TILES: The majority of glazed and unglazed tiles have negligible natural moisture expansion that does not contribute to tiling problems when tile are correctly fixed. However, with unsatisfactory fixing practices and in certain climatic conditions, natural moisture expansion may aggravate problems, especially when tiles are directly fixed to inadequately aged concrete substances. Source: ISO 10545-10.

NOTE: Regular Quality Control Audits ensure continuing compliance to the Standard although minor variations can occur in some values from batch to batch, within the allowable tolerances. These specifications will be re-issued if major variations occur, for example with the installation of new manufacturing equipment.